

Technical data

MOLYSLIP X12 Fluid

The logo for MOLYSLIP, featuring the brand name in a bold, italicized, sans-serif font with a registered trademark symbol, set against a red rectangular background.

Moisture displacing corrosion preventative

Description

MOLYSLIP X12 Fluid is a specially formulated moisture displacing corrosion preventative designed to provide long term protection of metallic components (upto12 months indoor storage / short term outdoors).

MOLYSLIP X12 Fluid is based on a unique blend of high quality corrosion inhibitors, oils and waxes specially selected to deposit a moderately thin oil like film which facilitates ease of removal prior to either secondary operations or components being put into service.

The applied film of MOLYSLIP X12 Fluid has self-healing properties which protects against removal by accidental scuffs, scrapes and handling of components during storage.

MOLYSLIP X12 Fluid is Barium free.

Features and benefits

- Provides environmental protection during transport and storage
- Dewatering capability facilitates application to damp surfaces
- Superior wetting gives a consistent even coating and reliable protection
- Self-healing film provides protection from incidental damage
- Easily removed prior to secondary operations
- Not classed as flammable for storage or transport
- Barium free

Packaging

20ltr

Molyslip Atlantic Limited, 4 Huntsman Drive, Northbank Industrial Park, Irlam, Manchester, M44 5EG, UK
Tel: +44 (0)161 804 4700 Fax: +44 (0)161 804 4701 enquiries@molyslip.co.uk www.molyslip.co.uk

Company registration number: 02664511; Company registered in England VAT registration number GB578295191

Technical data

MOLYSLIP X12 Fluid



Instructions for use

Shake well before use.

MOLYSLIP X12 Fluid is supplied ready for use.

MOLYSLIP X12 Fluid can be applied by brush, dip or low pressure spray in a well ventilated area. For maximum protection ensure a complete and thorough coating.

Note: Components should be clean, dry and free of contamination prior to application. After application components should be allowed to drain and the carrier solvent evaporate so that the desired film can form prior to packaging or storage

Technical data (typical values)

Property	Test method	Result
Appearance	MSTM 1	Opaque green liquid
Density @ 20°C	MSTM 23	0.82 g.cm ³
Non-volatile content	MSTM 57	20%
Flash Point	ASTM D93	>60°C
Film thickness	MSTM 63	2.5μ
Salt fog	ASTM D117	42hrs
Coverage	MSTM 64	75 m ² /l
Protection period	-	upto 12 months

Storage

Store MOLYSLIP X12 Fluid out of direct sunlight.

Storage temperature should be controlled to between 5°C and 35°C.

The product information in this publication is based on knowledge and experience at the time of printing. There are many factors outside our control or knowledge which affect the use and performance of our products, for which reason it is given without responsibility.
Issue date 02-22

Molyslip Atlantic Limited, 4 Huntsman Drive, Northbank Industrial Park, Irlam, Manchester, M44 5EG, UK
Tel: +44 (0)161 804 4700 Fax: +44 (0)161 804 4701 enquiries@molyslip.co.uk www.molyslip.co.uk

Company registration number: 02664511; Company registered in England VAT registration number GB578295191